

	ABS	ASA	PA	PBT	PBT+PC	PC	PC+ABS	PC+PBT	PE	PET	PMMA	POM	PP	PPO	PPO+PS	PS	PVC	SAN	TPU
ABS	V	V	BV	V	V	V	V	V	BV	BV	V	BV	BV	BV	BV	BV	V	V	V
ASA	V	V	BV	V	V	V	V	V	BV	BV	V	BV	BV	BV	BV	BV	V	V	V
PA	BV	BV	V	BV	BV	U	U	U	BV	BV	BV	BV	BV	U	BV	BV	U	BV	V
PBT	V	V	BV	V	V	V	V	V	BV	BV	BV	BV	BV	BV	BV	BV	U	V	BV
PBT+PC	V	V	BV	V	V	V	V	V	BV	BV	BV	U	BV	BV	BV	BV	U	V	V
PC	V	V	U	V	V	V	V	V	BV	V	V	U	BV	BV	BV	BV	U	V	BV
PC+ABS	V	V	BV	V	V	V	V	V	BV	V	V	BV	BV	BV	BV	BV	U	V	V
PC+PBT	V	V	U	V	V	V	V	V	BV	V	V	BV	BV	BV	BV	BV	U	V	V
PE	U	U	BV	U	U	BV	U	U	V	U	U	U	V	U	BV	U	BV	U	BV
PET	V	V	BV	V	V	V	V	V	BV	V	BV	BV	BV	BV	BV	BV	U	V	BV
PMMA	V	V	BV	BV	BV	V	V	V	BV	BV	V	U	BV	BV	BV	BV	BV	V	BV
POM	BV	BV	BV	BV	BV	U	U	U	BV	BV	U	V	BV	BV	BV	BV	BV	BV	BV
PP	U	U	BV	U	U	U	U	U	BV	U	U	U	V	U	BV	U	BV	U	BV
PPO	BV	BV	BV	BV	BV	BV	BV	BV	BV	BV	BV	BV	BV	V	V	V	U	BV	BV
PPO+PS	BV	BV	V	BV	BV	BV	BV	BV	BV	BV	BV	BV	BV	V	V	V	U	BV	BV
PS	BV	BV	BV	BV	BV	BV	BV	BV	BV	BV	BV	BV	BV	V	V	V	BV	BV	BV
PVC	V	V	U	U	U	U	U	U	BV	U	V	V	BV	U	BV	BV	V	V	V
SAN	V	V	BV	V	V	V	V	V	BV	BV	V	BV	BV	BV	BV	BV	V	V	BV
IPU	V	V	V	BV	V	V	V	V	BV	V	V	V	BV	BV	BV	BV	V	V	V
V = verträglich BV = bedingt verträglich U = unverträglich																			
horizontal = Überschlußkomponente																			
vertikal = Mischungskomponente																			